

MIDDLE LAYER - TECHNICAL DATA

	Standard	Unit	Result
Species of wood	Pine		
Glue type	PVAc (D3;D4); EPI		
Density	EN 323	kg/m ³	291
Bending strength	EN 310	N/mm ² long gr.	1,9
E - module	EN 310	N/mm ² long gr.	131
24 h swelling in thickness	EN 317	%	0,5
Thermal conductivity, λ	EN 12667	W/mK	0,085
Withdrawal of screws	EN 320	N (from plane)	330
		N (from margin)	380